









Product properties	
Format	2200 x 185 x 13 mm
Top layer	≥ 2.5 mm
Packaging	9 Elements
Pack	3.663 m ² / 26.163 Kg
Pallet	32 Packs 117.216 m ² / 837.216 Kg
Warranty	25 years
Notes	- cleaning an maintenance see intruction - technical changes reserved

Product labeling	
       	Only laquered products:

Tolerances (EN 13489)	
Admissible difference in length (± 0.1 %)	± 0.05 %
Admissible difference in width (± 0.2 mm)	± 0.1 mm
Squareness of the element (≤ 0.1 %)	≤ 0.05 %
Longitudinal curvature along the element (≤ 0.1 %)	≤ 0.05 %
Transverse curvature across the width (≤ 0.1 %)	≤ 0.08 %
Height differences of elements (≤ 0.2 mm)	≤ 0.18 mm
Moisture content at the time of first delivery (5-9%)	6 – 8 %

Classification Specifications			
		Prüfnorm	Bewertung
	Resistance to roller castor chairs	EN 425	We recommend the use of a conventional chairmat
	Effect of a furniture leg	EN 424	No visible changes
	Thermal conductivity Underfloor heating – suitable, with the backing material an vapor barrier	EN 12664	0.087 m ² *K/W
	Formaldehyde (E1 = 0.1 ppm)	EN 717-1	≤ 0.05 ppm
	Accoustical impact noise reduction	ISO 717-2	12 db (with Akustic-Protect 100)
	Disposal		Privat waste disposal with normal haushold waste, bulky waste possible

Classification surface properties				
		Testing standard	Valuation	
			Lacquer	Natuoroil
	Slip resistance	EN 13893	μ ≥ 0.47	μ ≥ 0.47
		CEN/TS 15676	29 SRT (SRV wet)	46 SRT (SRV wet)
			51 SRT (SRV dry)	103 SRT (SRV dry)
	Reaction to fire, click-installation as a floating floor	EN 13501-1	D _{fl} s1	
	Reaction to fire, installation by all-over adhesion	EN 13501-1	D _{fl} s1	
	Chemical resistance	EN 13442	Category 5	Category 4
	Bond strength / Gross cut test	ISO 2409	0	n.n.
	Slip reststance, inclined plane	DIN 51130	R 9	R 10

Changed:	QMB	File name:	PA_TDS_Parkett_Eco Balance_EN_2015
Date:	01.08.2013	Update:	www.parador.de
Our TDS will be constantly updated and adapted to the prior art. This version replaces all previous versions and is valid from:			
			01.01.2015

Free sorting according to EN 13489							
Assortment:	Block						
Characteristics according to EN 1310:	Upper side of the lamella						
Type of wood:	Beech	Oak			European walnut		
Botanical designation / Code (EN 13556):	Fagus sylvatica L. / FASY	Quercus petraea Liebl., Quercus robur L. / QCXE			Juglans nigra L. / JGNG		
Origin:	HU, HR, SK, BA	DE, AT, HU, HR, SK, BA, UA, RS, FR, CZ			US		
Shortcut / sorting / date (internal):	ER-L-BU		ER-L-EI			ER-L-SWN	
	Version 7 2014		Version 7 2012			Version 6 2012	
	A2	A4	A2	A4	N4	A2	A4
Sorting:	Natur	Living	Natur	Rustikal	Living	Natur	Living
Sound sapwood	-	-	not permitted	permitted	permitted	permitted: 30 % sapwood-lamella per cover layer	permitted: 70 % sapwood-lamella per cover layer
Knot (intergrown)	permitted: up to 15 mm	permitted: up to 20 mm	permitted: up to 15 mm	permitted: up to 20 mm	permitted: up to 30 mm	permitted: up to 20 mm	permitted: up to 30 mm
Falling out knot	not permitted	not permitted	permitted: up to 10 mm	permitted: up to 20 mm	permitted: up to 10 mm	not permitted	not permitted
Pinkknots	permitted	permitted	permitted	permitted	permitted: Cluster of knots	permitted	permitted
Filling	permitted: up to 10 mm	permitted: up to 10 mm	permitted: up to 10 mm	permitted: up to 20 mm	permitted: up to 10 mm	permitted: up to 10 mm	permitted: up to 20 mm
Slight crack/ haircrack	not permitted	not permitted	not permitted	not permitted	not permitted	permitted	permitted
Sugar inclusions, mineral inclusions	-	-	-	-	-	-	-
Bark pocket	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted
Lightning cracks	permitted	permitted	not permitted	permitted	permitted	not permitted	permitted
Slope of grain	all features permitted	all features permitted	all features permitted	all features permitted	all features permitted	all features permitted	all features permitted
Healthy heart	permitted	permitted: brown lamella	-	-	all features permitted	-	-
Medullary ray	permitted	permitted	permitted	permitted	permitted	-	-
Discoloration, colour variation	permitted	permitted	permitted	permitted	permitted	permitted	permitted
White streaks	-	-	not permitted	permitted	permitted	-	-
Pilling sticks marking	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted
Biodeterioration (EN 1311)	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted
Non-visible parts							
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.							
Comment							
Maximum 3% of lamellas are allowed in the next lower grading. Wood is a natural product and therefore different in color and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.							

Changed:	QMB	File name:	PA_TDS_Parkett_Eco Balance_Anhang_EN_2015
Date:	01.08.2013	Update:	www.parador.de
Our TDS will be constantly updated and adapted to the prior art. This version replaces all previous versions and is valid from:			01.01.2015
			Page 1 of 2

Free sorting according to EN 13489			
Assortment:	Wide plank		
Characteristics according to EN 1310:	Upper side of the floor board		
Type of wood:	Oak		
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE		
Origin:	DE, AT, HU, HR, SK, BA, UA, RS, FR, CZ		
Shortcut / sorting / date (internal):	ER-LH-EI	ER-LH-EI	ER-LH-EI thermo.
	Version 4 2011	Version 4 2012	Version 1 2012
	N3	N7	N4
Sorting:	Classic	Rustikal	Living
Sound sapwood	not permitted	permitted	permitted
Knot (intergrown)	permitted: up to 30 mm	permitted: up to 80 mm	permitted: up to 50 mm
Falling out knot	permitted: up to 15 mm	permitted: up to 30 mm	permitted: up to 30 mm
Pinkknots	permitted: Cluster of knots	permitted: Cluster of knots	permitted: Cluster of knots
Filling	permitted	permitted	permitted
Slight crack/ haircrack	not permitted	permitted	permitted
Sugar inclusions, mineral inclusions	-	-	-
Bark pocket	not permitted	-	not permitted
Lightning cracks	permitted: cracks in knots	permitted	permitted
Slope of grain	permitted	permitted	permitted
Healthy heart	not permitted: core tube	permitted	permitted
Medullary ray	permitted	permitted	permitted
Discoloration, colour variation	permitted: slight color variation	permitted	permitted
White streaks	-	permitted	permitted
Pilling sticks marking	not permitted	not permitted	not permitted
Biodeterioration (EN 1311)	not permitted	not permitted	not permitted
Non-visible parts			
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.			
Comment			
Maximum 3% of lamellas are allowed in the next lower grading. Wood is a natural product and therefore different in color and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.			

Changed:	QMB	File name:	PA_TDS_Parkett_Eco Balance_Anhang_EN_2015
Date:	01.08.2013	Update:	www.parador.de
Our TDS will be constantly updated and adapted to the prior art. This version replaces all previous versions and is valid from:		01.01.2015	Page 2 of 2